



Technical Datasheet Arbo 925 Primer

Arbo 925 Primer is a one part, solvent containing, air-drying isocyanate resin based primer.

Main Applications

Recommended for use in conjunction with Arbokol AG2 and Arbokol 2150 two-part polysulphide sealants for the priming of asphalt and bituminous surfaces.

Application Instructions

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate Arbo Cleaner. Apply one coat of Arbo 925 Primer using a clean dry brush and allow it to dry for a least 1 hour but not more than 8 hours before applying the sealant.

All joint preparation and priming should be carried out in accordance with BS 8000 Part 16, the British Standard for the sealing of joints in buildings using sealants.

Technical Data

Colour: Yellowish

Density: Approx 1.15 g/cm³

Application Temperature: + 5 ° C to + 30° C

Cleaning: Tools must be carefully cleaned immediately after use with an appropriate cleaner.

Joint Size Suitability

The joint width should be at least 6mm in order that the joint faces can be cleaned and primed correctly.

Storage Life

9 months in original unopened package stored in a cool, dry place out of direct sunlight.

First Issue: 26.06.08

1/2



Health & Safety

Arbo 925 Primer is labelled as Harmful and Highly Flammable. For full information please refer to Material Safety Data Sheet

Packaging

Arbo 925 Primer is supplied in 500ml tins (yield approximately 125 metres per 500ml)

Important: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.

Adshead Ratcliffe. Derby Road, Belper, Derbyshire DE56 1WJ, England.

Telephone: 01773 826661 Fax: 01773 821215

www.arbo.co.uk