

Cl/SfB	Yt4
CAW P22	
Uniclass L675:P743	

Description

FA160 is a gun grade, neutral cure silicone sealant with fungicide.

Colour

Lead grey

Packaging

310 ml cartridge (20 per carton)

Technical Information

Property	Test Method	Results
Composition		neutral cure silicone sealant with fungicide
Specific Gravity		1.01
Consistency	ISO 7390, profile U20	non-sag
Shore A Hardness	ISO 868	18
Skin Forming Time	at 23°C, 50% RH	10 minutes
Tack Free Time		Approximately 30 minutes
Cure Rate	at 23°C, 50% RH	1-2 mm/day
Tensile Strength	ISO 8339	0.4 MPa
Modulus at 100%	ISO 8339	0.3 Mpa
Elongation		
Elongation at Break	ISO 8339	200%
Movement		± 25%
Accommodation		
Elastic Recovery	ISO 7389	95%
Application Temperature		+5°C to +40°C
Service Temperature Range		-40°C to +120°C
Storage		Store in dry conditions between +5°C and +25°C.
Shelf Life		12 months when stored as recommended in original unopened containers.

Necessary Tools

- Cartridge gun and sharp knife.

Priming

- FA120 has excellent primerless adhesion to many typical construction materials. For special situations, or if in doubt, please contact tremco illbruck Technical Services Department to discuss your requirements.


Joint Design Considerations

- Joint design to be in accordance with BS 6093.
- For the purposes of joint width calculation in BS 6093, the MAF of FA120 is 25%.
- Width to depth ratio of illbruck FA120 should be 2:1.
- Minimum depth of 6mm on non-porous substrates and minimum depth of 10 mm on porous substrates.
- Sealant width not to be less than sealant depth.
- For fillet joints, the minimum bite onto each surface should be 10 mm for porous substrates and 6 mm for non-porous substrates.



FA160

Lead Sealant



Usage / Purpose

FA160 Lead Sealant is specifically formulated for sealing lead flashings into chases cut into brick, stone and concrete around external building and roofing features. The product is chemically compatible with most construction materials and cures to give a finished joint that is superior to traditional mortar based solutions in terms of seal quality, lifetime, movement accommodation and appearance.

Key Benefits

- Excellent adhesion to lead, masonry and brickwork
- Cures rapidly to provide a permanent flexible seal
- Long-term resistance to weathering, ageing and UV

Surface Preparation

- Joint faces should be clean, dry and free from dust, oil, grease, old sealant and any traces of contaminant which may affect adhesion. Any previously applied sealant must be mechanically removed.
- Thoroughly clean with a suitable cleaning solvent using the two cloth method, using one cloth dampened with the cleaning product to lift contaminants and a second clean dry cloth is used to remove any cleaner residue.
- Apply masking tape to prevent contamination of adjacent surfaces.
- Contact tremco illbruck Technical Services Department for further information if required.

Joint Backing

- Deep joints should be filled with an approved material such as illbruck FM617 360° PU Foam. In movement joints, back fill the joint with polyethylene joint backing in order to control the depth of sealant and prevent three-sided adhesion.

Application

- Always carry out a test application to prior to installation, to confirm compatibility and suitability for use.
- Application should be in accordance with BS 8000:16 - "Code of practice for sealing joints in buildings using sealants".
- Apply between +5°C and +40°C using a conventional skeleton gun or electric/power equipment.
- All beads should be tooled after application to ensure firm, full contact with the joint faces.
- Tooling should commence without delay due to the rapid skinning of the product.

Coverage

Width x Depth (mm)	Linear metres per 310 ml Cartridge
6 x 6	8.6
10 x 6	5.2
10 x 10	3.1
20 x 10	1.6
25 x 12	1.0

Fillet Joint Width x Depth (mm)	Linear metres per 310 ml Cartridge
6 x 6	17.0
10 x 10	6.2

Cleaning

Remove excess sealant immediately with AT200 High Strength Cleaner. Ensure surface is solvent resistant before cleaning. Cured sealant can only be removed mechanically.

Please Note

May discolour when in contact with bitumen, or asphalt or marble. Lead flashings must be securely wedged before application of the sealant. Do not use in permanently submerged joints. Do not apply to surfaces that are in direct contact with food. Not recommended for fixing mirrors.

Health & Safety Precautions

Safety data sheet must be read and understood before use.



Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products.

For more detailed information, service and advice, please call Customer service on 01942 251400.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which

has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for information provided in this leaflet although it is published in good faith and believed to be concerned. tremco illbruck Limited reserves the right to alter product specification without prior notice, in line with Company policy of continuous development and improvement.



tremco illbruck Limited
Coupland Road, Hindley Green
WN2 4HT Wigan
T: +44 1942 251400
F: +44 1942 251410

uk.info@tremco-illbruck.com
www.tremco-illbruck.co.uk